

RAMANI RANJAN CHOWDHURY (Mica Specialist)

HANDBOOK OF MICA

Being a comprehensive treatise in six parts, dealing with Natural and Built-up Mica and Mica Products in all aspects, including Geology, Prospecting, Mining, Production, Manufacture, Utilisation and Marketing of Mica.

By

RAMANI RANJAN CHOWDHURY

(Mica Specialist) Author of "India Mica", etc., etc.

" * * * In a very real sense, our vast electrical development is a monument to mica,—the one indispensable di-electric. The history of the intensive electrification that has been in progress during the last three decades, is the history of the modern mica industry * * * ".— J. V. LEWIS.

> CALCUTTA THACKER, SPINK & CO. (1933), LTD.

> > LONDON W. THACKER & CO. 8 & 9, Ludgate Square, E.C. 1939

PRINTED FOR THE AUTHOR BY THACKER'S PRESS & DIRECTORIES LTD., CALCUTTA, AND PUBLISHED BY THACKER, SPINK & CO. (1933), LTD., CALCUTTA. $\times 9 (F 3 | 4|) I$ 9 13211

OTHER BOOKS BY THE SAME AUTHOR

1. India Mica, Vol. I. Price Rs. 5 inland; 7s. 6d. or \$2.00 foreign, exclusive of postage. To be had of the Economic Supply Agency, Post Box 11437, Calcutta, and other important booksellers in Calcutta.

2. Prospects of the Cane Sugar Industry in Bengal with a Foreword by John D. Nikas, General Manager, Messrs. Carew & Company, Darsana, Bengal. Price Rs. 2 net. To be had of the Economic Supply Agency, Post Box 11437, Calcutta, and other important booksellers.

3. Mica Directory and Who's Who in Mica (under preparation).

For opinions see at the end of this book.

All rights reserved.

PREFACE

Since the publication of "India Mica", Vol. I, in February 1932, friends from different parts of the globe urged me to expedite publication of Vol. II, in which I proposed to deal with the international aspects of mica. In view of the great slump in world trade, I decided to wait till a more opportune time. Since 1934, when business once more took a hopeful turn, the trade in mica improved and reached an unprecedented level in 1937, and in these favourable circumstances I have revised my plans and decided to write a comprehensive and up-to-date "Handbook of Mica".

Those who are interested in mica, particularly the mica vendors in India, are, in many cases, not in touch with the world's markets for the demand and supply of mica. The Indian dealers are also often not acquainted with the technique and other essentials of the industry. This is particularly true in regard to their study of the consumer's point of view. These factors are believed to be responsible for much of the abuses that have appeared in the mica trade during the last decade, resulting in a loss of confidence amongst important buyers. India now stands to lose in her international trading if she does not re-organise her mica industry on a more satisfactory basis. Previously India had no rivals in the supply of ruby muscovite mica, which had been her monopoly since about 1884. Now, however, she has seriously to reckon with competition from several muscovite-producing countries, such as South and East Africa and South America. Russia, the earliest and once the only supplier of muscovite mica to Western Europe and North America, has been re-organising her extinct mica industry and her output is already sufficient for her greatly enlarged domestic requirements. The time must shortly come when the proportion of Russian sheet mica production will increase and leave an exportable surplus. India has very little time to lose for re-organising her industry, but if this is carried out on an economic basis, she may still retain the advantages in regard to the preparation, classification and processes

Preface

of her mica products. In order to hold the premier position as the largest world supplier of sheet mica, it is necessary for the Indian mica industry to increase its efficiency by cutting down productive costs in all branches of the business, such as mining, manufacture and marketing, without impairing the technical side of the management.

The successful exploitation and development of the national resources of a country largely depend upon the availability of the requisite information regarding the extent, economic character and working facilities for the interested public, but India is very poorly equipped in this respect. The United States of America, Canada, etc., have moved far ahead in this direction and the Bureaux of Mines and Commerce of these countries regularly collect useful information and publish the same in cheap official information circulars, memoirs, bulletins, etc. Mica is a subject very seldom treated by general writers, or by scholars or technicians and the literature on it is very fragmentary and scattered. In India, the only sources of information are the Records and Memoirs of the Geological Survey of India. A few officers of this Department, including the distinguished geologist Sir Thomas Holland, have earnestly interested themselves in this mineral and as a result of the experiences of the Great War (1914-18), attention has been more widely directed to the survey and potentiality of this mineral reserve. A detailed official survey of the reserves of mica in Bihar is already in progress, which is expected to be completed in about a year or two. The Indian public, and mica men in particular, have so far cared very little to derive benefit from these publications; the methods followed in the mining of mica and mica manufacture are greatly wasteful and unscientific. Attempt has been made in the present monograph to treat the subject in a systematic manner and bring together, in one comprehensive volume, all that a mica man needs to know from the practical point of view.

In the preparation of this handbook, and in the study of the subject, I have received valuable guidance and assistance from numerous friends, publishers, authors and contributors of periodicals, journals and papers as also from the various publications of the Geological Survey and Mines Departments of the Governments of India, United States, Canada, Union of South Africa,

Preface

etc., to all of whom I acknowledge my indebtedness. I am particularly grateful to the officers of the Geological Survey of India, specially Dr. A. M. Heron (Director), Dr. Cyril S. Fox, Dr. M. S. Krishnan and Dr. J. A. Dunn. I am also grateful for valuable help to Prof. P. N. Ghosh, Head of the Department of Applied Physics, University College of Science, Calcutta. Without this valuable guidance and assistance offered to me, I could not have accomplished my task. Special mention is also to be made of Messrs. Jaroslaw's Erste Glimmerwaren Fabrik in Berlin, Mr. William Brand, Jr., New York, Major W. I. Anderson of the Associated Insulation Products Ltd., London, Mr. F. C. Chrestien and Mr. W. G. G. Richards of Messrs. F. F. Chrestien & Co., Ltd.

I must also record my indebtedness to Mr. R. S. Carter of Thacker, Spink & Co. (1933), Ltd., and Mr. J. F. Parr of Thacker's Press & Directories, Ltd., Calcutta, for the courtesy and attention that I have received from them during the preparation and publication of this handbook.

> RAMANI RANJAN CHOWDHURY. Post Box 11437

Calcutta, 1939.

V

CONTENTS

PART I

PAGES.

Chapter

Rocks of the earth ; The mother rock of mica; Source of commercial sheet mica; Countries of comparative geological stability; Formation of secondary mica or sericite ; The origin of the pegmatites and the formation of mica ; Secondary minerals in the igneous rocks; Muscovitisation of the pegmatites; Difference between mica schist and gneiss ; The mineralogy of the mica pegmatites; The erratic occurrence of the pegmatites; The erratic occurrence of the pegmatite; The vein or fissure, pocket and contact deposits; Micas of commerce; Muscovite or the granitic mica of commerce; The kaolinisation of the muscovite mica; The nature of mica deposits in India; Quality of the Bihar mica; Special features of the Madras mica belt; The phlogopite or the pyroxenite mica of commerce.

Chapter

II Physical Characteristics and Chemical Composition of Micas

Percussion and pressure figures; Nomenclature; Different groups and types of micas; Muscovite; Paragonite; Zinnwaldite or lithium-iron mica; Lepidolite or lithia mica; Phlogopite or magnesium mica; Biotite or magnesium-iron mica; Lepidomelane or ferric-iron mica; Roscoelite or vanadium mica: their association, occurrence and colour; Commercial and noncommercial micas; Fuchsite or chrome mica; Lefferisite; Physical properties of muscovite, phlogopite, lepidolite and other micas; Chemical tests; Optic axial angle; Commercial ingurities of mica; Chemical composition of different types of micas from various sources of occurrence; Pleochroism in mica; Hardness of mica; Thermal resistance of different micas at elevated temperatures; Importance of capillarity in mica; Heat resistivity of mica; 16-41

Chapter II—concld.

Mica insulation for boiler and steam pipes; Mica in electric insulation; Mica a munition of vital strategic importance; Comparison of several di-electrics; Di-electric constant and power factor measurements of mica; Di-electric testing of micas; Mica in modern transport engineering.

PART II

THE PRODUCTION OF MICA

Chapter

III Prospecting and Development

Advantage of glaciation in prospecting; Effect of topography in India; Prospecting in the alluvial plains; Methods of prospecting; Tunnels in prospecting; Characteristics of prospective pegmatites yielding sheet muscovite; Difference between the modes of occurrence of muscovite and phlogopite micas; Indicative value of quartz and feldspar in tracing prospective mica deposits; Special features of the Madras mica deposits; Helpful hints in prospecting for muscovite mica deposits; The surface mining or "Uparchala" working in India; Mica, a mineral of deep-seated (igneous) origin; Size of mica crystals; Development in mica mining; Classification of mica mines; No general rule in mica; Future of the worked-out mines.

Chapter

IV The Mining of Mica . . Crude mining in India; Introduction of modern mining; Mining in Bihar; Crude method of hoisting; The ancient mica miners, the 'Labenas' and 'Yenadis'; The modern mining methods; Open-cut mining or open quarrying; Underground mining bv stoping; Overhand and underhand stoping; stoping; Overhand and underhand stoping; Mining of vein and pockety deposits; Ideal muscovite mica mining in U. S.; Open-cut mining; The winning of mica; Hand-drilling and machine-drilling; Drilling for sheet and scrap mica; Power drills; Cost of drilling; Blasting; Lighting; Hoisting; Cable derricks and aerial rope-ways; Haulage; Power for traction; Reclamation of mica; The Khalaktambi Mica Mine, Kodarma, India.

Chapter

V The Economics of Mica and the Problem of Wastage

Wastage in different processes of treat-ment; Proportion of "R.M." and "S.D.B." mica to total block; Mica content of

58-73

74-95

PAGES.

42-95

42--57

Chapter V -concid.

pegmatite and percentage of commercial yield in India; Government mica mining at Jorasemar (1918-19); Cost of production at Jorasemar; Wastage and commercial yield in U. S.; Cost and recovery of mica in U. S.; Proportion of mined sheets and rock in different countries Consta and rock in different countries,-Canada, South African Union, Rhodesia, East Africa (Tanganyika), Brazil; Place of supervision in a mica business; Mill flow-sheet for reclamation of mica.

PART III

OCCURRENCE AND DISTRIBUTION OF MICA

• •

• •

Chapter

Chapter

VI Mica in India Mica in Hindu chemistry and medicine: Early history of the modern mica industry; Types of Indian productions; Dumps in India and dump-cut splittings; Indian mica, known as *Bengal mica* in international trade; Export figures give a nearer reliable guide to find Indian production; India's position in the production of sheet mica; Cost of production and manufacture; How to reduce the overhead expenses in mica; Smallness of capital; Status of a mica merchant; Standardisation by a uniform nerronant; Standardisation by a Uniform all-India legislation; Madras mica trading; Reduced production of mica in Madras; Production, exports and imports; Mica during World War (1914-18); Mica as a munition material; Stability and prices; Co-operative marketing; The Bihar mica belt: Its special features, important mica mining centres and pioneers; Importance of Bihar mica deposits; Lithium mica in Bihar; Mining rent and royalty; The Madras mica belt: Its special features, important mining centres and pioneers; Important minines; Mining rent and royalty; Mica in Travancore State, Rajputana, Coorg Travancore State, Rajputana, Coorg Administration, Central Provinces, Nand-gaon State, Bastar State; The Punjab, Gwalior, Shahpura, Patiala; Jaipur, Jhabua, Kishengarh, Sirohi, Rewa State, Udaipur State (Mewar), Jashpur State: Mayurbhanj, Bamra, Gangpur and Bonai; Mysore State; Mica in Burma. **VII** Mica in Foreign Countries

Asla: Mica in Chosen, Japan, Ceylon, China, Cochin China, Aighanistan, Tibet: America : United States (Early history and method of mining; Types of production; Sheet and scrap; Statistics of production, 135-189

96-189

96-134

. .

PAGES.

Chapter VII-concid.

imports and consumption; Origin of tariff on imported mica; Distribution); Canada (Early history: Phosphate boom and the Canadian superphosphate industry; Nature of deposits and methods of mining; History of some large Canadian mica mines; "Lacey", "Blackburn", "Wallingford", "North Hill", "Lake Girard or Wakefield", etc.; Notable mines in Canada); Guatemala, Bolivia, Peru, Mexico, Newfoundland, Bolivia, Peru, Mexico, Newfoundland, Costa Rica, Chile, Argentina, Brazil; Africa: Madagascar, Union of South Africa; Rhodesia, Somaliland Protectorate or Anglo-Egyptian Sudan, Kameron Islands, Kenya Colony or East African Protectorate, Protectorate of South-West Africa, Namaqualand, Mozambique or Portuguese East Africa, Ethiopia or Abyssinia, Nyasa-land Protectorate, Tanganyika Territory; Oceania: Australia, Queensland, Tasmania, New Zealand, New South Wales; Eurasia: U. S. S. R. or Soviet Russia (Russia in relation to India as world supplier of muscovite mica, proportion of sheet and scrap, important localities of commercial micas; imports); **Europe**: Austria, Germany, Portugal, England, Norway, Sweden, Rumania, Czechoslovakia; Production of lithia or lepidolite mica; Abstract of World Occurrences of Mica.

PART IV

COMMERCIAL PREPARATION OF MICA

190-237 190-209

Chapter VIII Manufacture of Block Mica

Commercial qualifications ; Commercial defects or imperfections; Cobbing of mica in the mine and factory; Commercial preparation of mica for the market; Advantages of "S.D.B." mica; thumb-trimmed mica and its disadvantages; Wrong sickle-dressing of mica; Importance of sorting; Shear trimming; Rotary trimmer and mechanisation of splitting of mica; Shipment quality mica; Splitting blocks; Flow chart showing the process of preparation of mica in an average Indian mica factory; Flow chart of the processes of treatment of mica in Canada, prior to marketing; Sorting of mica : different commercial qualities; Green ruby (Madras) mica; Black mica; Classification of mica in U. S. A.; Bengal ruby mica as standard-ised in U. S. A.; Muscovite ruby mica standards in London; Classification of Canadian amber and Madagascar phlogopite

PAGES.

Contents

Chapter VIII—concld.

micas; Classification of mica in Brazil; USES OF MICA AND THE FORMS IN WHICH IT IS MARKETED.

Chapter IX Standard Gradings of Mica ... The Bengal system of sizing mica; Bengal standard gradings; Chart for classifying mica into the Bengal grades; The middle averages of the Bengal grading; "Fit-cut" mica and "cut mica" of random thickness; Condenser films; The Madras system of sizing mica; U. S. system of grading; Canadian system of grading; Madagascar and Chosen grading systems; Comparative standard sizes of mica-producing countries.
 Chapter X Manufacture or Commercial Preparation of the system o

X Manufacture or Commercial Preparation of Mica Splittings and Films History of the development of mica splitting process; Large-size sheet mica getting scarce even now; Rifting of mica, a manual operation; Origin of splitting manufacture in India; Different packings of splittings; Process of manufacture of splittings; Marketable grades of book-form splittings; pan splittings; G. E. C's specifications; Loose-packed splittings; Dust or powder loose splittings; Madras round-cut splittings; Home-splitting system; Splittings in the United States; Mica splitting machine; Mica splittings in Canada; Mechanisation of splitting operation; Splittings in Madagascar.

PART V

UTILISATION	OF	Mica and	Mica	
Products	••	••	••	238299
Built-up Mica	1 01	Micanite		2 38–255

Chapter XII Built-up Mica or Micanite ... History of invention of built-up mica; Points of importance in built-up mica manufac228-237

218-227

210-217

Pages.

256-267

268-275

Chapter XII—concld.

ture; Process of manufacture of micanites; Mechanisation of the operation of laying Moulding insulation (or cone plates); Flexible mica insulation; Heater mica insulation; Coil insulation (mica folium); Micanite paper, mica cloth or mica linen; Composite mica paper; Rope paper and mica; Mica paper and presspahn; Mica asbestos; Art mica plate; Mica tapes; Mica paper tape; Mica silk tape; Mica paper silk; Mica linen tape; Mica tubes; Insulation binder; Difference between glyptal and shellac for use in built-up mica manufacture.

Chapter

XIII Testing and Specifications of Mica and Micanites

Mica an efficient insulator for high voltage work; Specifications for electric insulation; Mica for magneto condensers; Mica for radio and wireless outfits; Stove mica; Commutator segment mica; Diaphragm mica; Micalite or chimney mica; Mica for the manufacture of splittings; U. S. Government specifications for purchase of mica and micanites; Detailed specifications for uncut mica; Test on natural sheet mica; Detailed specifications for cut mica; Detailed specifications for sheet micanite or built-up mica sheet; Mica splittings for built-up mica; Binding material for micanite manufacture; Di-electric strength of mica plates; Detailed specifications for grade A mica plate (commutatoris for grade A mica plate (commutatori segment plate): grade B mica plate (moulding mica plate); grade C mica plate (flexible or cold moulding micanite); Di-electric testing of mica plates; Pressure test on commutator micanite (grade A plate); Commercial specifications for mica splittings; Standard specification of a large British user of mica splittings; Specifications of ground mica

Chapter XIV Associates, Inclusions and Substitutes of Mica

Sericite; Vermiculite; Steatite or talc and serpentine; Associated rocks and minerals; Mica schist; Chlorite schist; Feldspar; Apatite; Tourmaline; Tantalite and columbite; Beryl; Xenotime; Triplite: Pitchbiende and uranium ochre; Substitution of mica; Pertinex; Turbonite; Dellite; Micarta; Mycalex; Artificial production of mica.

xii

Contents

Chapter

XV The Electrical Uses of Mica*

Introduction; The electrical properties of mica; The di-electric strength; The dielectric constant; Volume resistivity and temperature variations; Power factor; A summary of the characteristic properties of mica; Uses of mica for small commutator segments; Mica for condenser insulation; Mica for sparking plug insulation; Mica for insulating washers.

PART VI

MARKETING OF MICA

Chapter XVI The Technique of Mica Marketing ... Middlemen's role; Mica brokers; Ware-houses in London; Large and small buyers or consumers of mica; Terms of business; Packing; Marking; Mica manufacturing and marketing centres; London's importance in the international mica trade; Price of mica.

Chapter XVII The International Mica Trade: World Demand and Supply of Mica . .

Resources in mica of the different powers; Sheet mica; Splittings; Scrap mica; Strategic situation of the great powers in respect of mica resources; Great Britain; United States; Germany; France; Italy; Russia and Japan.

Chapter XVIII The Present and Future Outlook of the Indian Mica Industry: A Retrospect

Standardised trading and co-operative marketing; Domestic utilisation of mica in India; Government and mica industry; Recommendations.

*Contributed by Dr. P. N. Ghosh, Sir Rash Bihari Ghosh Professor of Applied Physics, University College of Science, Calcutta.

314-319

300-319

300-306

. .

307-313

PAGES. 276-299

xiii

APPENDICES

Appendix	I Code for mica industry in the United	Page.
Appendix	States	320
Appendix 1	I Approximate charges of warehousing and clearances in important foreign marketing centres	322
Appendix I	I Currencies, weights and measures in different countries	324
Appendix N	Tariffs on Mica	325
Appendix V	W "NEMA "* specifications of mica splittings	327
Appendix V	T Prices of mica Facing	328
Appendix V	II World production of mica—Statistics Facing	332
	ILLUSTRATIONS	
	Frontispiece Facing	iii
Figure I	Pegmatite of Jorasemar Facing	12
Figure II	The Hazaribagh mica schist country, Jorasemar	14
Figure III	Percussion figure	17
Figure IV	Pressure figure	17
Figure V	Uparchalla (open-cut), Jorasemar, Kodarma	51
Figure VI	Top of shaft, Jorasemar, Kodarma	52
Figure VII	Gutiya (open-cut), Jorasemar, Kodar- ma	53
Figure VIII	The Khalaktambi Mica Mine, Kodarma Reserve Forest	95

• "NEMA" = The National Electrical Manufacturers Association of America.

Appendices

Figure IX	Cutting abod and sights drassing space	Page.
rigure IA	Cutting shed and sickle-dressing opera- tion	194
Figure X	Mica cutters at work at Domchanch	195
Figure XI	Showing the right and wrong dressing of S.D.B. mica	197
Figure XII	Manufacturing mica splittings, J. Podger's Mica Factory at Kodarma	224
Figure XIII	Manufacture of micanite in India	242
Figure XIV	Sorting of mica splittings by English girls	243
Figure XV	Micanite Ring Department, Waltham- stow Works, London	247
Figure XVI	Di-electric strength of different types of mica	278
Figure XVII	Volume resistivity of muscovite mica	280
Figure XVIII	Series of arrangements for condenser sections	286
Figure XIX	Clamp with single insulated end for mica condenser	2 88
Figure XX	Central terminal principle for con- densers	2 89
Figure XXI	Condenser clamp with central terminals	289
Figure XXII	Ring condenser insulation	290
Figure XXIII	Mica bushing	2 91 ·
Figure XXIV	Mica bushing, special type	292
Figure XXV	Lodge sparking plug	2 94

CHARTS AND MAPS

Mineral Map of	India	••	••	c é	113
Chart for classify	ving mica	into Bengal	grades	• 1	211

APPENDIX I

CODE FOR MICA INDUSTRY IN THE UNITED STATES*.

A Code of Fair Competition for the mica industry was submitted and approved by the Administrator for the Industrial Recovery on 24th February, 1934. The Code consists of 10 articles, which are summarised as follows :---

Article I-states the purposes of the Act.

Article II-gives definitions and sets forth the following five divisions of the mica industry :-

- (a) The mining division.
 - (b) The importing division.
 - (c) The sheet-mica division.
- (d) The wet-ground mica division,
- (e) The dry-ground mica division, including grinders of shop or scrap mica, grinders of mica schist and those recovering mica from clay washing.

The manufacture of plate and other built-up mica is operating under the Code of Fair Competition for the electrical manufacturing industry.

Article III--deals with the working hours and comprises of six sections, summarised as follows :--

- (i) No employee shall work more than 40 hours a week nor more than 8 hours a day, provided however that for six weeks in any six-month period, an employee may work 48 hours a week.
- (ii) Outside salesman, executive or manager earning not less than \$35'00 a week is not restricted as to working hours. Emergency maintenance or repair works are limited to 48 hours per week.
- (iii) Engineers, firemen and cleaners may work 48 hours a week and not over 56 hours during any six weeks of any 6-month period.
- (iv) Watchmen may work 54 hours a week.
- (v) No employer shall permit any employee to work for a time which if totalled with working time expended with another employer in the industry would exceed the maximum allowed by the Code.
- (vi) No employee shall work more than 6 days in any seven-day period.

Article IV—this article specifies the minimum wages shown in the following table in the different divisions of the industry in two geographical sections, which embraces Alabama, Florida, Georgia, Kentucky, Mississippi, North Carolina, South Carolina, Tennessee and Virgina, and the

* Mica in 1934, U. S. Bureau of Mines Year Book.

Appendix

Northern Section which includes all other states and territories of the United States :--

Minimum housely magon in the

	minimum nourly wages in the mica industry.		
	Southern section.	Northern section.	
	\$	\$	
1. Mining division	025	0 30	
2. Importing division	0°30	0.35	
3. Sheet-mica division	025	· 0 [•] 30	
4. Wet-ground mica division			
in grinding operations	0°30	0.35	
in other operations	0.25	0.30	
5. Dry-ground division-			
in grinding operations	0.275	0.325	
in other operations	0.25	0.30	

Article V--states that no person under 16 years of age shall be employed in the industry nor any person under 18 years of age in work which may be hazardous or dangerous to health.

Article VI—establishes a national code authority, consisting of the chairman of the division code authorities and not more than three other members appointed by the Administrator but without vote. It also defines the duties and powers of the code authority.

Article VII—establishes a divisional code authority of five members in each division of the industry and specifies how the members shall be elected and their duties and powers under the general supervision of the national code authority.

Article VIII—outlines a code of definite competitive practices and provides for the drafting of rules and regulations by the divisional code authority to make the code effective.

Article IX-provides for enforcement of the provisions of the code with the arbitration of the disputes within the industry.

Article X—guarantees that the employees have the right to organise and to bargain collectively through their representatives and that they shall not be required to join any company union. It also provides for cancellation or modification of the code by the president and allots one vote in the affairs of the mica industry to each corporation, partnership or individual who is a member of the code and provides that it becomes effective the second Monday after its approval by the president.

The writers of the chapters on mica in the Minerals Year Book observed on the effects of the code over the mica industry as follows :--

"It is difficult to predict the total economic effects of the code, but the short-time results will doubtless be increased wages, shorter hours and a probable increase in employment. Hearings on the code brought out that mica miners received 10 cents an hour and worked 50 to 60 hours a week, compared with the established 25 cents hourly wages and 40-hour week under the code."

H. M

APPENDIX II.

Approximate Charges of Warehousing and Clearances in Important Foreign Centres.*

(a) WAREHOUSE CHARGES ON MICA IN LONDON.

		1†	2†	3†
1.	Landing (receiving ex steamer, London; land- ing and housing).	min.: 5 tons	1s. 1½d. per cwt.	15s. per ton.
2.	Customs clearance			
	Weighing at landing or delivery.			
4.	Port dues	1s. per ton.	1s. per ton.	1s. per ton.
5.	Rent per week	9d. per ton.	11d. per ton.	
б.	Sampling (opening, nailing and closing).		1s. 10d. per case.	1s. 6d. per case.
	Sampling while open Sampling opening and delivery within city limits.	2s. 6d. per	8d. per case.	
7.	Inspection		1s. 10d. to 2s. 6d.	1 <i>s</i> .
	Where contents removed from case and replaced.			2s. 6d.
8.	Port marking, etc., minimum 6d.	6d.	6d. per score of letters.	3d. per score of 20 letters less 10d.
9.	Delivery to van		7d.	
10	Warrant stamps, if		3d. per	6d. per
	warrants are issued.		warrant.	warrant.
11.	Dock dues		none.	none.
	Customs entry	5.		5s. per con-
~	cubionic chilly	v 3.	99	signment.
13.	Cartage			none.
14.	Fire		6 per cent.	5 per cent.

(b) STORING OF MICA IN NEW YORK.

Merchandise can be stored under bond, without the payment of duty, for three years, and then duty paid only on that part which is withdrawn and put into consumption.

The storage should be made in warehouses adjacent to the piers, to keep down delivery expenses and cheap rates of insurance should be tried for. The important storage companies are :---

The New York Dock Co., Brooklyn, N. Y.

The Bush Terminal Warehouse, Brooklyn, N. Y.

The Ponch Terminal, Staten Island.

†1. 2 and 3 represent the rates of three different wharfingers.

^{*} Some of the rates shown are not current as they are subject to variation from time to time, but they would give an average idea of the nature of charges incurred.

Appendix

and until full delivery is taken, there will be only storage rates and the first month is the only month that the labour rate is charged for. The merchandise is, of course, covered by fire and sprinkler insurance. This ranges from about \$2.78 per \$1,000 to \$3215 per \$1,000 depending on the particular warehouse the mica will be stored.

The original charge for entire handling is generally in the neighbourhood of \$00 which, of course, depends on the value or size of the shipments and quotations may be asked for at a set price of \$00 per shipment for the original entry.

As the drawals are made, duties may be paid either by the customer or by the exporter's agent and the wharfingers may attend to the shipments depending on their size for \$2.00 to \$3.00 per shipment. This includes all incidentals.

Warehouse Keepers in New York.

TOWER'S WAREHOUSE, INC., N. Y.

PENSON AND COMPANY, NEW YORK

(c) MICA SHIPMENTS; EXPENSES AT HAMBURG.

1. Landing charges by Hansa Line-Rm. 0045 per 100 kg.

2. Rent for storage on wharf (by Hansa Line)— Rent 2 days free.

"	6	**	additional	Rm.	0.05	per	100	kg.	per	day.
	24	n			0.03			,,		.,

After	32	**	 ,,	0.01	,,	"	,,

3. Delivery from wharf-Rm. 0.3 to Rm. 0.05 per 100 kg.

4. Transportation from wharf to warehouse-

			Rm.				Rm.
Up to 3,000	kg.		0 ⁵⁰ per	100 kg.	. not less	than	10 00
3,000/5,000		••	C*40	**	"	"	15.00
5,000/7,500	,,		0.35	**	**	"	20.00
7,500/10.000	,,		0.30	,,	,,	*	26°25.
10,000/15,000	.,		0.22	37	**	,,	30-00
15,000/20,000	"	••	0 ⁻ 22	29	>3	**	37 50.

5. Receipt or delivery of warehouse--Rm. 022 per 100 kg. up to 50 tons. 0.16 per 100 if more than 50 tons.

6. Weighing-Rm. 010 per 100 kg.

7. Warehouse rent-Rm. 0.10 per 100 kg. per month.

8. Clearance charges-1 per cent. of the goods value.

- 9. Insurance premium (for { against fire only-02 per thousand. against usual risks-1 per thousand.
- Commission, postages, telephone and cable charges, etc., not included.
 Per thousand of the goods value for endeavours regarding receipt, warehousing, storage, in s u r a n c e, delivery, collection and remittance.

(d) MICA SHIPMENT LOCAL CHARGES AT ANTWERP.

- 1. Reception from steamer on quay-Fcs. 11 plus 21 per 1,000 kilos.
- Cartage from steamer to railway station or to warehouse— Fcs. 4250 plus 2½ per cent. per 1,000 kilos. Cartage from warehouse to railway station—Fcs. 4250 plus 2½ per cent. per 100 kilos.
- 3. Warehouse rent-Fcs. 5 per 1,000 kilos and per month or part of month.
- Customs clearance—These expenses depend upon the importance of the consignment with a minimum of fcs. 100 per sending.
 Postage and petties—Fcs. 5, fcs. 750 or fcs. 100 per sending.
 Watching expenses eventually payable to the import steamer.

APPENDIX III.

CURRENCIES, WEIGHTS AND MEASURES IN DIFFERENT COUNTRIES.

English and Metric equivalents.

1 pound (avoirdupois)* =16 oz. or 4536 grammes. 100 lb.=4536 kilos. 112 lb.=5080 kilos. 1 long or English ton =2,240 lb. =1,016 kilos. 1 short ton =2,000 lb.	1 inch = 25.40 mm. 1 foot = 30.48 cm. 1 yard = 91.44 cm. 1 mile = $(1.780 \text{ yds.}) = 1609.35$ cm. 1 sq. inch = 6.4516 sq. cm. 1 sq. foot = 0.0929 sq. metre. 1 sq. yard = 0.6361 sq. metre. 1 stone = 14 lb. = 6.3503 kilos.
= 907.2 kilos. 1 metric ton	
=1,000 kilos.	1 millimetre $= 0.03937$ inch.
$= 2,204^{\circ}6$ lb.	1 centimetre = 0.3937 inch.
=0.9842 gross ton.	1 meter = 39.37 inches
= 1.1023 short tons.	$= 3^{\circ}2808$ feet.
1 kilos = 2.2046 lb.	1 kilometre == 0.62137 miles.
100 kilos = 220.46 lb.	= 1,093.6 yards.
1 maund (<i>i.e.</i> , Bengal maund)	1 sq. mm. $= 0.00155$ sq. inch.
$= 82\frac{2}{5}$ lb. 1 quintal = 100 kilos = about 225 lb.	1 sq. cm. = 0.155 sq. inch. 1 sq. meter = 10.7639 sq. ft.
r_1 quintar = 100 knos = about 223 lb. or 2.6 mds.	r sq. meter = 107039 sq. 11. = 1°196 sq. yds.
or zo mas.	Jus.
Inch. $mm. \\ 0.006 = 0.15$	mm. Inch.
0.006 = 0.15 0.008 = 0.20	0.01 = 0.0003937
0.010 = 0.25	0.01 = 0.0015748
0.015/16 = 0.40	0.1 = 0.003937
0.020 = 0.50	0.5 = 0.0019685
0.024 = 0.60	4 = 0.15
0.028 = 0.70	25 = 1
0.032 = 0.80	FF0 201
0.036 = 0.90	$550 = 39\frac{1}{2}$ $570 = 22\frac{1}{2}$
$\begin{array}{rcl} 0.040 & = & 1.00 \\ 0.056 & = & 1.40 \end{array}$	370 = 222 $1000 = 39\frac{1}{2}$
0.050 = 1.50	$1030 = 40\frac{1}{2}$
0.080 = 2.00	1070 = 42
0.120 = 3.00	· · · · · · · · · · · · · · · · · · ·

*1 pound troy (for gold, silver, jewellery, etc.) is equal to 12 oz. or 373 242 grammes.

CURRENCIES

Approximate equivalent based on exchange Re. 1 = 1s. 6d, sterling.

Country.	Coin.	Approximate.
United States	Dollar	= 4s. 1td.
Argentina	· Argentine · Peso	= 19s. 10d. = 4s.
Brazil	Milreis	= 2s. 3d.
Bolivia	Boliviano	= 2s.
Germany	Reich Mark	= 11 ³ <i>d</i> . to 1 <i>s</i> .
France and Suisse	Franc	$= 9\frac{1}{2}d.$
Italy	Lira	$= 9\frac{1}{2}d.$
Norway, Sweden	and	
Denmark	Kroner	$= 1s. 1\frac{1}{5}d. \\ = 1s. 8d.$
Netherlands	Fulden (florin)	
Belgium	Franc	$= 9\frac{1}{2}d.$
Austria	Kronen	= 10d.
Russia	Rouble	$= 2s. 1\frac{1}{3}d.$
Spain	Paseta	= 1s. 9½d.
Portugal	Escudo	= 45.
Madagascar		French currency
Rumania	Leu	$= 9\frac{1}{2}d.$
Japan	Yen	$=$ 1s. $0\frac{2}{3}d$.

APPENDIX IV.

TARIFFS ON MICA.

United Kingdom.— Mica not mentioned in the tariff; presumably free. Canada.—Mica is not specifically included in the Canadian Customs Tariff but comes under general item No. 711. See p. 146.

Belgium.-Mica crude in sheets, plates or rough mica-free. Mica in leaves, sheets or cut,

for electrical machinery-5 per cent. ad valorem.

for stores, shades, fans, etc., and sheets for machinery other than electrical-5³/₂ per cent. ad valorem.

others-171 per cent.

Great Britain .-- Mica is free.

Germany.—(i) Raw mica, raw plates or discs—free. (ii) Artificially coloured or ornamented cut sheets of mica—10 marks on every 100 kilos. Uncoloured or undecorated cut sheets—2½ marks per 100 kilos.

Czechoslovakia.—Ores free, mica plates (glimmer and mikanit platten).—21 Czech crowns (for most favoured nations) per 100 kilos. Manufactures of mica (glimmer-und mikanit warin).—

(i) Combined with "ordinary" materials-512.5 Czech crowns with 3 per cent. tax.

(ii) Combined with "fine" materials-1,080.0 Czech crowns plus 13 per cent. tax.

Sweden.-Mica crude-free. Manufacture of mica free.

Holland .- Mica not mentioned in the Tariff; presumably free.

Denmark .- Duty of 3 per cent. ad valorem.

Madagascar.--3 per cent. export duty on a valuation fixed by government.

Netherlands.-Mica blocks and splittings admitted free. Micanites-3 per cent.

Handbook of Mica

Italy.-In lump, powder or scales-free. For imports of mica or scale, no duty. Mica in plates unworked or merely cut-free. Surtax 2.50 per cent. ad valorem.

Switzerland.-Mica raw or in squares, not cut out-per quintal, 30 cents. In squares or sheets, cut out or in frames combined or not with tissues, metals, etc.-5 francs. Not pierced or otherwise worked, per 100 kilos-8 francs. Worked, per 100 kilos-30 francs. Wares of mica not otherwise specified, even combined with paper.

Australia.--Crude mica in slab-20 per cent. ad valorem. Mica and manufactures thereof-30 per cent. ad valorem plus a primage duty of 21 per cent. ad valorem. Mica not mentioned in the tariff; presumably free as "other earths and mineral substances, not specifically mentioned, crude, burnt, ground or washed" (Item No. 110B).

New Zealand.-Mica from British countries free and from foreign countries-25 per cent. ad valorem plus 9/40ths surtax. No export tax.

Spain.—Mica schist or works even with parts made of other materials: First tariff, 80 pasetas per 100 kilos. Second tariff, 20 pasetas gold per 100 kilos. Second tariff is always applied.

United States .- Dealt with on p. 146.

France.-Import duty on sheets or plates of mica, articles of mica, micanite or compressed mica, micaceous paper or cloth even mixed with other material.

Mica in regular morsels, standard size, shape or of specific forms weighing up to 5 grammes per unit—48 per cent. ad valorem. Others per 100 kilos—800 francs* net weight[†].

Japan.-Mica and manufactures thereof, not otherwise provided for-

- (a) In slab or powder-free.
- (b) (i) In sheets, uncoloured or unornamented—free.
 (ii) Others—ad valorem 25 per cent.
- (c) Sheets glued together or mica glued on tissue paper, etc .--100 kin ‡ 38·10.
- (d) Others-ad valorem 20 per cent.

India.-No export duty on any mica sent out of India.

*1,000 grammes equal to 1 kilogram or 2.2046223 lb.

+ Mica from Madagascar free from duty.

t Kin equal to 160 momme, equivalent to 1.32277 lb. avoir., or 1.60754 lb. troy.

NEMA grade.	Standard commercial grading.	Size.	Thick- ness in inches per 10 films.	Manufacture.	Remarks,	
	E. M. 4-10 : muscovite splittings.	•				
A	No. 5—1st quality B. F.; P. P.; loose with powder; loose.	Standard No. 5† commercial grading (3 in. to 74 sq. in.).	0-007 0-009	Must be evenly split to specified thickness; no thick edges or cor- ners; absolutely clean cut films.	Must be clean films; sound musco- vite mica; free from all spots and stains.	
B	No. 51-1st quality B. F.; P. P.; loose with powder.	Standard No. 5½ commercial grading (1½ in. to 2½ sq. in.).	0.007 0.009	Same as A	Same as A.	арре
С	No. 5 1 —2nd quality; loose with powder; loose.	Do.	0.007 0.010	Evenly split to thick- ness and as above, but edges may be slightly uneven.	Same as A.	appenuts
D	No. 6—1st quality; loose with powder; loose.	At least 60 per cent. of splits to be full standard No. 6 (1 to 13 sq. in.), balance to pass over 3-in. mesh screen.	0.007 0.009	Same as A	Same as A.	
E,	No. 5—2nd quality	At least 50 per cent, of splits to be full standard No. 6, balance to pass over a 3-in. mesh screen.	0.007 0.010	Same as C	Must be clean films; sound musco- vite mica containing not more than 5 per cent. slightly weathered or earth-stained films. No mineral stains permissible.	
F	No. 6—3rd quality; loose	Splittings shall be of a minimum area of § sq. in. and, should pass over a ½-in, mesh screen.	0-008 0-012	Same as C	Must be clean films; sound muscovite mica containing not more than 74 per cent. slightly weathered or earth- stained films. No mineral stains.	

APPENDIX V. NEMA* specifications for standard mica splittings (muscovite).

National Electrical Manufacturers Association of the United States. Adopted standard 8th December, 1932.
 † No. 5 grade should be large enough to cut rectangular pieces measuring 1½ by 2, 2 by 2 and 2 by 2½ inches, etc., and thus, instead of total area, rectangular area in each grade is to be looked, for.

NEMA grade.	Standard commercial grading.	Size.	Thick- ness in inches per 10 films.	Manufacture.	Remarks.
	E. M. 4-15 : phlogopite (amber) splittings.				
M.	No. 4—1st quality B. F.; P. P.; loose with powder; loose.	No. 4 standard grading (6 to 9% sq. in.).	0•007 0•009	Must be evenly split to specified thickness; no thick edges or cor- ners; absolutely clean cut films.	mineral inclusions and must with- stand heat of 300 degree C. without
N	No. 5-1st quality B. F.; P. P.; loose with powder; loose.	No. 5 standard grading (3 to 5 ⁷ / ₂ sq. in.).	0·007 0·009	Same as M	Same as M.
0	No. 6-1st quality; loose with powder; loose.	At least 60 per cent. of splits to be full standard No. 6*, balance passable over ‡-in. mesh screen.	0-007 0-009	Same as M	Same as M.
Р	No. 6—2nd quality; loose	At least 50 per cent. of splits to be full standard No. 6, balance passable over ½-in. mesh screen.	0.007 0.009	Evenly split to thick- ness and as above, but edges may be slightly uneven.	Same as M.

APPENDIX V—concld.

									(P	er	1Ь.	Unr in	fED ates	.Kı lin	NG Ki	CX-	warc	hot	BC.)							H (Per l	амт 5, іт	urg n st	erling.)	Uniti (Duty paid	to STATES.	dollars
			19	13-	-14			15	19-	-20			19	29_	30			19	32-	-33			1	1937			1914	19	20	1933	1929	1933-34	1936
Specia	l grade: CLSS. F.S. G.S. Std. B.S.	s. 13	d. 6	to ••		d . 0	s. 16 16	• 0		8. 37 26 24 19	đ. 0 0 0	s. 24 19 12 10	0	to 2	14	d. 0 0 0 6	s. 6	d. 0	::	4. 17 7	d. 6 9	s.	d.	···	3.	d.	s. d. 16 6 13 9 9 ^{°°} 7	24	d. 0 0	<i>s. d.</i> 43 2 28 9 17 3	7-20-13-58 6-25 4-85	8·29 6·79 6·04 5·29 2·22	12.64 10.54 8.40 7.54 2.29
A-1	grade: CLSS. F.S. G.S. Std. B.S.			::	10 8	7 1	26 16			28 16 24 19	0 0 0 0	14 12 10	0 9 6	to to to	24 20 13 11	0 0 0 6	6	0	 to	17 7	6 9 [.]	30 21 13 12	0	to to to	28 15	00000	12 10 10 7 8 1		000	28 9 20 2 15 7	4.50-5.50 4.85-5.85 5.10 2.50	6·79 5·44 5·29 4·09 2·14	₹ 5.89 4.84 2.21
No. 1	grade: CLSS. F.S. G.S. Std. B.S.	8 6	9 6	to to	8	3 0 4	20 16 12	0	to to to	18	0 0 0 6	19 12 11 10 8	6 6	to to to to	20 13 12 11 8	0 0 0 0 6	14 11 9 4	0 0		16 11 9 6	0 6 9 0 0	25 14 12 11	0	to to to	18 13	00000	10 8 9 3 7 4	34 20 12	8 	23 0 13 3 9 [°] 9	5.0-5.75 3.0 2.75 2.05	4·24 3·64 3·12 2·89 1·99	8·44 4·09 3·09 3·34 2·06
No. 2	grade: CLSS. F.S. G.S. Std. B.S.	7	4	to 	5	3 0 9	15 9		to to	13	0 6 0	16 9 9 8	0	to to to	17 10 9 8 6	96666	12 9 6 3	0 6 0	to to to to	14 9 8 7 4	0 6 0 10	18 12 10 8	0	to : to :	16 11	0 0 0 0	9 3 7 4 6 0	30 19 10	0 0 	18 5 10 4 6 4	4.20 2.30 2.15 1.80	3·49 2·74 2·59 2·14 1·47	6.94 3.04 3.14 2.44 1.54
No. 3	grade: CLSS. F.S. G.S. Std. B.S.	6	9	to 	5 3	9- 3 6	12	0	to 	16 10 6	0 6 9	7 6 3	0	to to to	16 9 7 6 4	0 0 3 6 3	11 5 4 3	3 0 8	to to to	11 6 5 5 3	6 0 6 0 3	17 10 8 7	0	to :	15 12	00000	79 69 6`8	6	0 0 	14 0 8 1 5 4	3.60-3.80 1.50-1.85 1.45 1.18-1.50 0.90-0.95	2.89 2.29 1.99 1.62 0.99	5·14 2·89 2·74 1·84 1·09

APPENDIX VI(b). Approximate average prices of India ruby mica in foreign markets.

* Vide Mr. Richard Schroeder's leaflet on Mica and Mica Products, printed in 1933, by H. S. Hermann, Berlin, S.W.19.

Appendix

APPENDIX VI(c). Approximate prices of Indian splittings in foreign markets.

		ondon and Contir ces per lb. in ster		Amer (Duty paid in d	
	1929-30	1932-33	1937	1929	1932
ook Splittings- No. 4 No. 5-1st quality No. 5-2nd quality No. 6-1st quality No. 6-2nd quality	$\begin{array}{cccccccccccccccccccccccccccccccccccc$	s. d. s. d. 4 3 3 4 to 3 9 2 9 to 3 0 1 10 to 2 1 1 10 to 2 0 	s. d. s. d. 5 0 to 6 0 4 6 to 5 6 4 0 to 4 3 3 0 to 3 6 2 0 to 2 0	1.08 0.90-0.96 0.65-0.90 0.60-0.64 	0-93-1-20 0-83 0-75 0-50-0-60
n Splittings	$\begin{array}{cccccccccccccccccccccccccccccccccccc$	 2 0 to 2 3 1 9 to 1 11 2 0 1 3	$\begin{array}{c} & & & & & & & & & & & & & & & & & & &$	0.40 1.00 0.90 0.75 0.60-0.72 0.48-0.64 	••• •• •• •• ••
No. 4 No. 4 No. 4 No. 5 special No. 5 ordinary No. 5 ordinary No. 6-1st quality No. 6-2nd quality		$\begin{array}{c} & & & \\ & & & & \\ & & & & & \\ & & & & $	$\begin{array}{cccccccccccccccccccccccccccccccccccc$	 	
sold Splittings	$\begin{array}{c} & & & & \\ 0 & 10\frac{1}{2} \text{ to } 1 & 0 \\ 0 & 9 & \text{ to } 0 & 9 \\ 0 & 7 & \text{ to } 0 & 8 \\ 0 & 6 & \text{ to } 0 & 7 \\ 0 & 5 & \text{ to } 0 & 6 \\ 0 & 4 \\ \end{array}$	··· ··	$\begin{array}{c} & \ddots & 2 & 6 \\ 1 & 6 & \text{to} & 2 & 0 \\ 1 & 2 & \text{to} & 1 & 4 \\ 0 & 9 & 1 & \text{to} & 0 & 18 \\ 0 & 9 & 1 & \text{to} & 0 & 18 \\ 0 & 7 & 1 & \text{to} & 0 & 7 \\ 0 & 5 & \text{to} & 0 & 6 \\ 0 & 5 & 0 & 4 \end{array}$	0.60 0.36-0.38 0.24-0.26 0.20-0.30 0.18-0.21 0.13-0.15 0.09-0.11	0.75 0.45 0.35 0.23-0.25 0.175 0.13 0.10

APPENDIX VI(d).

Maximum price of Bengal ruby mica blocks in January 1918. (as fixed by British Ministry of Munitions, London).

Cando			r	RICES PER	LB. IN	517,841F	G, EX. WA	REAUUSE.			-		
Grade.	Size (area).	Clear Govt. stand.	Part stained Govt. stand.	2nd quality clear.	2nd quality part stained.	F. S.	Ordinary stained (rust and clay).	Densely stained.	B. S.	Soft white,	·		
Extra Ex. Spl. Ex. Special Special A.1 2 3 3 5, (Govt. std.)	36-47 ³ " 24-35 ³ " 14-23 ³ " 10-13 ³ " 6-9 ³ " 3-5 ⁴ "	s. d. 30 0 23 0 21 6 20 0 17 6 16 0 12 0 9 0 5 0 3 0	s. d. 25 0 21 0 19 0 17 6 15 0 13 6 11 0 7 2 4 0 2 6	<i>s. d.</i> 23 6 20 0 18 3 17 0 14 9 13 0 10 6 7 0 4 5 1 9	s. d. 22 6 19 0 17 6 16 6 14 3 12 6 10 0 6 4 2 1 6	s. d. 21 0 18 0 16 6 15 6 13 0 10 7 5 6 3 10 1 3	s. d. 200 0 17 0 15 6 14 6 12 0 9 6 9 9 4 9 3 0 1 0	s. d. 16 U 13 0 11 9 10 6 9 0 6 9 5 0 3 3 1 9 0 11	s. d. 15 0 12 0 10 0 9 0 7 6 5 3 6 6 3 2 3 1 3 9	s. d. 17 6 15 0 13 0 11 6 10 6 8 6 6 0 3 9 2 3 1 0	No. 4 up-4s. 9d. , 5 (white)-3s. 3d. , 5 (other qualities)-2s. 9d. , 6-1s. 9d.		

Handbook of Mica

WORLD PRODUCTION OF MICA (IN METRIC TONS).

(1) Sheet mica (including blocks, splittings and films).

1937 1936 1935 1934 1933 1932 1931 1930 1929 1928 1927 1926 1925 1924 1923 1922 1921 1920 1919 1918 1917 1916 1915							
	1914 191	913 1912	1911 1	1910 1909	1908	1907 1906	1905 Rei
India (exp.) (5) 14,598 9,028 7,204 4,716 2,932 2,389 2,691 4,212 5,897 4,850 3,937 4,569 5,065 3,561 4,232 2,192 1,650 3,887 3,002 3,046 3,178 2,779 1,514 2,014 1	1 2,058 3,1 9 298 50	501 52	2,487 1,5 53	,268 1,662 68 33	1,403 1 218 1	1,772 2,463 387 287	1,174
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$		111 5† 	· · · ·]	··· ··			
Oceania 85 21 45 122 43 30 26 27 25 7 7 4 3 3 3 1 4 1 18 1 21 Ceylon (exp.) 1 1 1 18 1 <td>6 12 .</td> <td>a</td> <td>••</td> <td>•• ••</td> <td></td> <td></td> <td> (1)</td>	6 12 .	a	••	•• ••			(1)
British Empire 15,163 9,258 7,407 5,009 3,126 2,497 2,968 4,665 6,492 5,878 4,872 5,307 5,920 4,555 4,768 2,446 1,916 4,533 3,499 3,469 3,848 3,396 1,754 United States 769 598 425 265 165 153 436 665 923 763 685 985 814 663 936 489 337 764 701 746 579 393 255		786 3,445 771 383		,336 1,69 5 1,123 821		3,159 2,750 486 546	1,174 420 (1)
	1		5 14 9	$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$	$\begin{array}{c} \cdot \cdot \\ 1 \\ 23 \end{array}$	··· 5 16	
Bolivia 92 .4 .23 .8 .1 .15 .217 .25	1	··· ·· ·· ·· ··		··· ·· ··		··· ··	$\begin{array}{ccc} & & & & (1) \\ & & & & (1) \\ & & & & (1) \\ & & & & (1) \end{array}$
Norway 41 44 56 170 105 103 48 53 59 85 8 42 23 25 10 1 2 31 97 66 39 24 22 Sweden <t< td=""><td></td><td></td><td>•• </td><td>··· ·· ··</td><td>1</td><td>· · · · ·</td><td> (1)</td></t<>			••	··· ·· ··	1	· · · · ·	(1)
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$			•••	··· ·· ··		··· ·· ··	:: (1) .:
Total foreign tries coun- tries 1,855 1,820 1,465 1,086 655 582 910 1,296 1,603 2,126 1,370 1,658 1,467 1,200 1,288 752 771 1,334 1,210 1,158 786 480 325	5 307 79	793 403	884 1,	,146 838	465	491 562	420
World total (sheet							
mica) $ 17,018 $ $ 11,078 $ $8,872 $ $6,095 $ $3,781 $ $3,079 $ $3,878 $ $5,961 $ $8,095 $ $8,004 $ $6,242 $ $6,965 $ $7,387 $ $5,755 $ $6,056 $ $3,198 $ $2,687 $ $5,867 $ $4,709 $ $4,627 $ $4,634 $ $3,876 $ $2,076 $	2,725 4,57	579 3,848	3,427 2,4	,482 2,533	2,086 2,	2,680 3,322	1,594
(2) Waste and scrap mica (including reclaimed) United States 22,864 19,015 17,107 7,004 7,941 6,388 6,008 6,109 5,675 7,041 5,699 6,391 8,793 4,273 7,308 6,026 2,338 5,193 2,956 2,019 3,111 4,026 3,592	2 3,285 4,82	829 2,927		3,689 (3 ,711	2,193 2	2,740 1,351	1,022 ((1)
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$		004 470	••	615 300 		· · · · · ·	$\begin{array}{c cccc} 1,022 & (1) \\ & (1) \\ & (3) \\ & (2) \end{array}$
$ \begin{array}{c c c c c c c c c c c c c c c c c c c $:: ::	··· (1)
24,812 19,998 20,723 20,582 23,152 14,671 7,531 7,433 12,665 14,401 10,469 9,551 14,335 8,512 10,534 8,903 2,797 6,920 16,454 14,141 16,435 5,107 3,971	3,825 5,83	833 3,397	3,665 4,	,304 4,011	2,193 2	2,740 1,351	1,022
Total (world) 41,830 31,076 29,595 26,677 26,930 17,750 11,409 13,394 20,760 22,465 16,711 16,516 21,722 14,267 16,590 12,101 5,484 12,787 21,163 18,768 21,069 8,983 6,050	6,550 10,41	412 .7,245	7,092 6,1	,786 6,544	4,279 5	5,390 4,673	2,616
(3) Lithia mica production							
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$					· · ·		
$\begin{array}{c cccc} \hline United \ States(b) & . & 1,234 & 1,126 & 1,151 & 654 & . & . & . & . & . & . & . & . & . & $		··· ·· ·· ·· ·· ·· ·· ·· ·· ·· ·· ·· ··				··· ·· ··	••
							··· } (
mica) 44,224 33,130 31,606 28,374 28,401 19,960 12,503 14,736 22,200 24,034 18,009 17,619 22,223 14,267 16,599 12,101 5,484 12,787 21,163 18,768 21,069 8,983 6,050			7,092 €,	,786 6,544	4,279 5	5,390 4,673	2,616
* Almost entirely scrap (M. I. 1936) but to be conservative sheet production estimated at 10 per cent from 1931 and 20 per cent production of Asiatic Russia and Japan taken as scrap.	prior to 1931.	•					
§ Lithia mica production in Canada nor separately shown.							
§ Estimated at 10 per cent of total production. 1902 to 1913—production amounted to 113 points. Decidentican in 5 previous year's instantiated to the first and life to the first second life to t							
 † Assumed as sheet. ‡ Production of Asiatic Russia and Japan taken as scrap. § Lithia mica production in Canada not separately shown. § Estimated at 10 per cent of total production. [] 1902 to 1913—production amounted to 113 point. [] 1902 to 1913—production amounted to 113 point. [] Production in 5 previous years amounted to 113 point. [] Jour. June 1922). a Not available. b Included formerly in serap. c) The Startistic side Minard Indexty Appundia 			•				
b Included formerly in scrap. (1) U. S. Bureau of Mines Statistic and Minestry Annuals.	• * * •		•		•		
b Included formerly in scrap. (1) U. S. Bureau of Mines Statistic and Minestry Annuals. (2) Imp. Inst. Bulletins.	1	in an encontin	velv				

				KODAR	MA AND	GIRIDIH N	MARKET	S (INDIA).							LOND	ON M.	ARKET.	•		
			RUBY MIXED er maund in	MICA BLOCK. rupees.)	-		•	. Si	PECIAL RUBY (Good stai	MIXED MICA ned to clear				Shipme	NT QUAL (Prices	ity mix per lb.	ED RUBY in sterl	BENGA ing.)	L BLOCK	. S.
and a state	1924	1927	1930 .	1931	1932	1937	1924	1927	1930	1931	1932	1937	1900	1901	1908	1911 (Jan.)	1912 (Sept.)	1914 (July)	.1918 (Oct.)	1919 (Average)
No. A-1 No. 1 No. 2 No. 3 No. 4		Rs. 800 to 950 600 to 700 500 to 600 400 to 475 325 to 375 225 to 275 120 to 160 75 to 90 50 to 65 10 to 20	650 to 700 520 to 600 400 to 450 300 to 375	Rs. 600 to 700 500 to 550 400 to 500 230 to 300 170 to 250 120 to 160 75 to 100 50 to 60 30 to 40 7½ to 15	Rs. 600 to 700 500 to 550 375 to 460 220 to 280 160 to 220 110 to 150 60 to 100 45 to 60 35 to 45 6 to 12}	Rs. 650 to 700 500 to 600 400 to 480 350 to 380 200 to 280 149 to 180 90 to 100 50 to 60 45 20 to 25	Rs. 1,200 900 700 600 520 420 300 140 85 50 24	Rs. 1,200 900 630 550 450 350 200 to 225 135 90 50 23	$\begin{array}{c} Rs. \\ 1,200 \\ 900 \\ 630 \\ 500 \\ 400 \\ 350 \\ 175 to 200 \\ 130 \\ 80 to 90 \\ 45 to 50 \\ 24 \end{array}$	Rs. 1,000 700 550 420 325 250 150 to 160 85 to 100 60 16	Rs. 1,000 750 550 400 320 250 150 80 to 90 50 to 60 14	Rs. 900 to 1,000 800 to 850 600 to 700 500 to 600 400 to 500 	$\begin{array}{cccccccccccccccccccccccccccccccccccc$	$\begin{array}{c} s. & d. \\ 5 & 0 \\ 3 & 2\frac{1}{2} \\ 1 & 3 \\ 0 & 7 \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\$	$\begin{array}{c} s. & d. \\ 13 & 0 \\ 10 & 2\frac{1}{2} \\ 6 & 11 \\ 5 & 11 \\ 4 & 5\frac{1}{4} \\ 3 & 2\frac{1}{2} \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\$	s. d. 6 9 5 5 4 5 3 1 1 0 0 5 	$\begin{array}{c} s. & d. \\ & \ddots \\ 8 & 7 \\ 7 & 8 \\ 5 & 11 \\ 4 & 51 \\ 2 & 0 \\ & \ddots \\ 0 & 6 \\ & \ddots \\ & \ddots \end{array}$	s. d. 9 0 8 21 7 9 4 7 2 9 4 7 2 9 4 7 4 7 5 4 7 5 4 7 5 4 7 5 4 7 5 4 7 5 6	$\begin{array}{c} s. & d. \\ & \ddots \\ 21 & 8 \\ 20 & 0\frac{1}{2} \\ 15 & 6 \\ 10 & 9 \\ 6 & 6 \\ 2 & 3 \\ & \ddots \\ & \ddots \end{array}$	29 5 15 0 12 0 8 3 4 9

Approximate average prices of Bengal ruby mica block.

APPENDIX VI(a).

Approximate average prices of the United States domestic mica*, New York. (Prices per lb. in dollars.)

		1908	1911	1913	1918	1920	1922	1925	19	26	19	27	19	928	19	29	193	2	19	34	19	37
Scrap	$1\frac{1}{2} \times 2$ in. 2×2 , , , , , , , , , , , , , , , , , ,	••	1-20-1-75 2-0-2-50 2-75-3-50 5-50-5-75 5-50-5-75 9-5-11-0 	0.035 0.12 0.30 0.70 1.15 1.35		0.10 0.51 0.84 1.25 2.04 2.37 3.85 4.0 5.0 7.0	0.06 0.15 0.35 0.75 1.35 1.75 1.35 1.75 a 3.70 a 3.70 a 	$\begin{array}{c} 0 \cdot 05 - 0 \cdot 08 \\ 0 \cdot 16 \\ 0 \cdot 30 \\ 0 \cdot 75 \\ 1 \cdot 25 \\ 1 \cdot 75 \\ 2 \cdot 35 \\ 3 \cdot 0 \\ 4 \cdot 50 \\ 4 \cdot 50 \\ 5 \cdot 0 - 8 \cdot 0 \\ 17 \cdot 0 - 30 \cdot 0 \end{array}$	Clear. 0.05-0.15 0.15-0.50 0.40-0.75 0.75-20 1.20-1.50 1.40-1.50 1.50-3.0 2.0-3.90 4.0-5.50 6.0-8.0 \$15.0	Stained. 0.03-0.15 0.15-0.25 0.12-0.40 0.30-0.75 0.65-0.90 1.01-40 1.25-1.70 1.60-2.25 2.0-3.0 2.50-3.0	Clear. 0·5-0·15 0·25-0·35 0·67-1·50 0·67-1·55 1·25-2·20 1·75-2·64 2·0-3·50 3·75-5·0 7·0-8·0	Stained, 0·4-0·13 0·20-0·25 0·15-0·35 0·30-0·60 0·60-1·30 0·10-1·75 1·50-2·0 1·75-4·25 2·50-3·0 0-25·0	$\begin{array}{c} Clear.\\ 0.05-0.15\\ 0.10-0.50\\ 0.40-0.75\\ 0.35-1.25\\ 0.75-1.75\\ 1.60-2.20\\ 1.50-2.64\\ 2.0-2.75\\ 2.75-4.0\\ 4.0-6.0 \end{array}$	Stained, 0.04-0.05 0.8-0.15 0.20-0.50 0.60-1.00 0.75-1.50 1.20-1.65 1.25-2.0 1.50-2.0 1.50-2.50 0-30.0	$\begin{array}{c} Clear.\\ 0\cdot04-0\cdot15\\ 0\cdot20-0\cdot35\\ 0\cdot35-0\cdot50\\ 0\cdot60-0.95\\ 1\cdot10-1\cdot60\\ 1\cdot50-2\cdot0\\ 1\cdot65-2\cdot15\\ 2\cdot5-3\cdot0\\ 3\cdot0-5\cdot0\\ 3\cdot0-5\cdot0\\ 4\cdot0-7\cdot0\\ \$10\cdot54 \end{array}$	Stained. 0·03-0·06 0·40-0·85 1·0-1·45 1·20-1·80 1·40-2·C 1·60-2·50 2·0-2·75 2·25-3·0 	$\begin{array}{c} \textbf{Clear.}\\ \textbf{0.03-0.04}\\ \textbf{0.10-0.20}\\ \textbf{0.25-0.38}\\ \textbf{0.30-0.70}\\ \textbf{0.80-0.90}\\ \textbf{0.80-0.90}\\ \textbf{0.80-1.25}\\ \textbf{1.0-1.45}\\ \textbf{1.25-1.75}\\ \textbf{2.0-2.50}\\ \textbf{3.0}\\ \textbf{3.0}\\ \textbf{11.90} \end{array}$	$ \begin{array}{c c} Stained. \\ 0 \cdot 02 - 0 \cdot 03 \\ 0 \cdot 8 - 0 \cdot 15 \\ 0 \cdot 10 - 0 \cdot 30 \\ 0 \cdot 20 - 0 \cdot 50 \\ 0 \cdot 40 - 0 \cdot 80 \\ 0 \cdot 60 - 1 \cdot 05 \\ 0 \cdot 90 - 1 \cdot 25 \\ 1 \cdot 65 - 2 \cdot 15 \\ 1 \cdot 5 - 1 \cdot 75 \\ \cdots \\ \end{array} $	Clear. 0.03-0.06 0.15-0.30 0.20-0.55 0.30-0.90 0.80-1.50 1.0-1.90 1.25-3.0 1.50-4.0 12.93	Stained. 0.02-0.04 0.08-0.20 0.124-0.40 0.50-1.00 0.50-1.00 0.75-1.60 1.20-1.75 1.25-3.0 	Clear. 0-054 0-104 0-277 0-541 0-766 1-086 1-905 2-841	Stained. 0.049 0.119 0.209 0.368 0.461 0.791 1.247 1.344 1.162 2.500
Groun D W	d— ry (ton) 'et (ton)	•••	••	••	•••			30·0-70·0 65·0-125·0	::	::	·	•••	••	••	24•0 76•0		24•0 76•0	••	22•0 90•0	••	\$23-0 	••

(a) Not available.

*Average price paid at mines for rough cobbed trimmed sheet of good quality split and sorted to cut the sizes indicated.

APPENDIX VI.

mica	(inch	uding	reclair	ned)														
6,026 2,859	2,338 457 2	5,193 1,722 5	2,956 2,153	679	3,111 1,060	4,026 1,080	3,592 379	3,285 540	4,829 1,004	2,927 470	3,187 478	3,689 615	3,711 300	2,193	2,740	1,351	1,022	(1) (1) (3) (2)
a	a	a	a	a	a	a. *												(2)
a 15	a 	a 	11,338	11,443	12,324	a 	.:		::	::	::		••	::		::	•••	(1)
8,903	2,797	6,920	16,454	14,141	16,435	5,107	3,971	3,825	5,833	3,397	3,665	4,304	4,011	2,193	2,740	1,351	1,022	
12,101	5,484	12,787	21,163	18,768	21,069	8,983	6,050	6,550	10,412	7,245	7,092	6,786	6,544	4,279	5,390	4,673	2,616	
nica _.	produ	ction																
	••								::			::		::	::			I)
••	••		••			•• 1		•• .	••	••	••	•• /		••		••	••	
										•••								
	• •				•••	••	••	••	••	••	••	••					••	11 ·
																		} ¢
	•••				· · ·									•••				
12,101		12,787		18,768		8,983	6,050		10,412	7,245	7,092	6,786	6,544	4,279	5,390	4,673	2,616	

ction estimated at 10 per cent from 1931 and 20 per cent prior to 1931.

· · · · ·

Jour. June 1922).

1 1

and 41 tons of scrap. statistics to comprise of 1,500 and 13,367 ong tons of blocks and splittings respectively

INDEX

A

Abhra, 17, 96. Abraki Pahar, 80. Abyssinia-see Ethiopia. Accessory minerals, 6, 17. Acquisition of lands, 318. Act. Bihar & Orissa Mica, 100. Aeroplane, 274. Afghanistan, 139. Air, as an insulator, 35. Air inclusions, 192. Aircraft, 34. Ajmere mica, 204. Alabama, 148. Albite, 5, 46. Alexandria mine, 66, 150. Amber mica, 23, 165, 203, 206. Amblygonite, 19, 184–185. Amphiboles, 4, 275. Analysis of mica, 27–28. of production, 87. Andalusite, 4 Apatite, 12, 15, 44, 174, 271. Apophyses, 181. Argentina, 162. Arnold mica mine, 66. Art mica plate, 252, Artificial production of mica, 274. Asbestos, 35. Associates, 268. Australia, 175. Austria, 183.

B

Bihar mica, 11, 43, 116, 121. Bilaspur, 129. Binder (binding ingredient), 254, 261. Biotite mica, 13, 19, 25, 136, 155, 176, 189. Blackburn mine, 153, 158, Black spotted mica, 202, 204, 206, Black stained mica, 202, 205. Blasting, 69. Block mica, 190, 204, 284. manufacture of, 190. Boiler insulation, 33. Bolivia, 161. Bombay Presidency, 133. Bonai State, 132. Bookform splittings, 221, Boyd Knob mine, 151. Brazil, 92, 163, 208. British Columbia, 3, 154. Brokers, 277 Buchanon (Clarissa) mine, 151. Built-up mica, 168, 218, 238, 283. Bureau of mine, 318. Burr Knob mine, 151. Buyers, 277,

С

Cable derricks, 70. Calcite, 15, 174. California, 148. Camerons (Kameron Islands), 171. Canada, 90, 153. Cape province, 169. Capillarity in mica, 32. Capital, smallness of, 46, 103. Centres of manufacture and marketing, 279. Ceylon, 137-138. Chaibee mine, 160. Charges of warehouses and clear-ance, 322. Charnockites, 125. Charpentier's theory, 3. Chart of classifying mica, 211. Chemical analyses, 16-20, 27-28. - influences, 31. tests, 24 Chile, 162. Chimney mica, 258.

China, 138-139. Chlorite schist, 270. Chosen (Korea), 135. Chota Udaipur, 133. Chowdhury, R. R., 41. Chrestien, F. F. & Co., Ltd., 58, 120, 122, 131, 133. Mining Co., Ltd., 73. Cigar box, 165. Circle, 142, 214. Clarissa (Buchanon) mine, 151. Classification of mica, 204-207. Clay stain, 192. Clear and slightly stained mica, 202. — green mica, 203. — mica, 202, 259. Climax mine, 258. Cloudland mine, 151. Cobbing, 193. Cochin China, 139. Code for mica industry in U. S. A., 320. Co-efficient of thermal expansion, 32. Coesum, 184. Coil insulation, 250. Coimbatore, 124. Colorado, 148. Colour of mica, 19-20, 22, 120, 125. Columbite, 44, 47, 272. Commercial defects, 191. — impurities, 26. — micas, 9, 20, 317. muscovite, 2. preparation of, 193. Commutator, 41, 273, 277, 282. ______ micanite, 263. - physical properties, 24. Complaints, 104. Composite mica paper, 251. Composition of mica, 16-20, 27-28. insulation, 283. Conductor, 35. Consumers, 277. Consumption, 276, 314. Contract deposit, 155. Coorg, 128. Co-operative marketing, 116, 314-318. working, 318. Copal varnish, 35. Corundum, 175. Costa Rica, 162. Costs, 81, 86, 89, 92, 102.

Cowee Black belt, 150. Cross-cutting, 43. Cross-grained, 191. Crown mine, 153. Crude mining, 58. Crushing strength, 24. Crystall of mica, 50-52, 175. — large, 14. Crystallisation of mica, 5-6. Currencies, weights and measures, App. III, 324. Custer mine, 153. Cut mica, 213. Cyanite, 4. Czechoslovakia, 184.

D

"D" mine, 123. Dark amber, 206. Darwin (Port), 170. Davis mine, 149, 150–151. Dealers, 103, 279. Dellite, 272. Deposits, classification of, 7. nature of, 11, 154. Development, 42, 53-54, 98, 174. Diaphragm mica, 176, 208, 258. Di-electric, 35. - constant, 36–38, 279. - strength, 22–24, 37–38, 261, 267, 278. - testing, 39, 260–263. Disc, 198. cutting, 208. Disruptive strength, 36. Distribution of mica, 96-189. ______ of mica production, 110. exports, 112. Dressing, 125. Dried fibre, 35. Drilling, 67-68. Dry grinding, 231. Dump, 49, 74, 99, 102. - cut splittings, 99. cutting, 102. - reserves, 48. Dust loose splittings, 224. bookpacked, 221. Duty on mica, 146, 156.

E

Index

England, 183. Equipment, 168. factory, 221. mining, 54. Ethiopia, 172 (also Abyssinia). Eureka mine, 150. Experiments in boiler insulation, 33. Explosives, 69. Export, 106-108, 114. distribution of, 112. statistics of, 100-101, 108.

F

Faguni mine, 118. Fair average, 212. stained mica, 103, 202, 204. Fan, 165. Fancy cutting, 191. Father Guay mine, 160. Feldspar, 1, 270. Firing appliance, 34 First-class mine, 53. Fissure deposit, 7. Fit-cut mica, 212, Fletcher mine, 150. Flexible mica plate, 248, 262. Flow sheet, 94, 200-201, Folium mica, 253. Formulæ, chemical, 27-28, Foster mine, 151. Fox, Dr. Cyril S., 11, 44, 181. France, 310. French mine, 150. Fuchsite mica, 20, 269. Future of worked-out mine, 55.

G

Gabbro, 4. Gangpur State, 132. Ganjam, 124. Gas Engine, 34. Gaya, 118. General Electric Co., 157. Geological aspects of mica, 1. Georgia mine, 148. German East Africa, 173. Germany, 183, 310. Ghosh, Prof. P. N., 276. Giridih, 208. Girod mine, 165. Glimalac, 255. Glory-hole mining, 157-158. Glyptal, 254, 298-299. Government of India, 317. Grading of mica, 210-217. Grand Parade mine, 170. Great Britain, 310. Great War, 178, 307. Green amber, 207. — clear, 203. Grinding of mica, 229, 236. process, 231–233. Ground mica, 228. — consumption of, 237. — covering capacity of, 235. Group management, 89–90, 318. Guay mine, 165. Gutiya mine, 53. Gwalior, 129.

H

Halides, 5. Hamilton mine, 151. Hammer mill, 268. Hard drill, 68. Hard-moulding micanite, 296. Hardness of mica, 22-24, 29-30. Haulage, 70. Hazaribagh, 117. Heat insulation, 248 —- resistance of mica, 32. —- resisting micanite, 398. Heater elements, 208. Heater elements, 208. Heater micanite insulation, 248. Heater elements, 208. Heater micanite insulation, 248. Heater justained mica, 206. Hematike, 275. Hibbs mine, 149. Hints on prospecting, 47. Hob Neil mine, 189. Holland, Sir Thomas, 4, 57, 318. Holometer, 33. Home-splitting system, 225. Hope mine, 185. Hornblende, 169.

· 1

Idaho, 149. Idol mine, 170. Igneous rocks, 1. Ilmenite, 174, 275. Imports, 107. statistics of, 144. Inclines, working by, 141. Inclusions, 268. India, 9. Mica, Vol. I, 197. Inikurti mine, 50, 124. International mica trade, 307. Insulation, 33-34. Insulator, 256. Isinglass, 17. Italy, 310. J

Jack hammer, 54. Jaipur, 130. Japan, 136–137, 311. Jaroslaw's Erste, 208–213, 305. Jashpur State, 131. Jeffersite, 21, 269. Jhabua State, 130. Jorasemar country schist, 14. mica mining, 77–78, 81, 117. pegmatite of, 12.

ĸ

Kalichedu mine, 123. Kameron Islands, 171. Kangra, 129. Kaolinisation of mica, 10. 16. Kefne mica field, 171. Kek grinder, 7, 232. Kenya Colony, 171. Keyes mine, 150. Khalaktambi Buriya mine, 73, 95. Kishengarh, 130. Knife trimming, 193. Kodarma, 117. Krishnan, Dr. M. S., 132.

L

Labenas, 59. Lacey mine, 156-157. Lagging, insulation, 33. Lake Girard mine, 160. Lakshminarain mine, 123. Lamp chimney, 168. Last Hope mine, 170. Leaders of mica, 7. Leduc mine, 161. Legislation, 104. Lena field, 179. Lepidolite (lithia mica), 5, 19, 25, 120, 120, 142, 142, 145. 130, 138, 142, 155. 161, 163, 164, 170. 176, 184, 187. Lepidomelane, 25, 189. Lepfynites, 126. Lethionite, 184. Lethiophlite, 5, 184. Light green mica, 203. Levi Anderson mine, 149 Leysdorp mica mines, 166. Lighting in mine, 69. Liquefaction of mica, 97. London, 279, 304.

Loose-packed splittings, 223. Loughborough Mining Co., 157.

M

Madagascar, 37, 164. Madras mica, 13, 46. ——— mica belt, 122. - round-cut splittings, 225. Magnesium mica, see phlogopite. Magneto condenser, 256. Mahajins, 59. Maine, 149 Malabar, 124. Mama deposits, 149. Manbhum, 118. Manufacture of built-up mica or micanite, 241. - of mica, 190. of splittings, 221–223. Marketing, 275. ----- centres, 304. - technique of, 275. Marking, 304. Mayurbhunj State, 132. McGie mine, 161. Metamorphic rocks, 1. Mexico, 162. Miami field, 169. Mica, a key commodity, 319. - a munition material, 34, 114. analyses of, 27–28. - artificial production of, 274. asbestos, 252. brokers, 302. bushing, 291–292. cambric, 297. cloth, 251. - condenser, 288. - crystals, 50–52, 175. ------ large, 14. di-electric strength of, 22–24 - directory*. - distribution of, 96-189. - economics of, 74. electrical uses of, 278. - films, 213. - folium, 250, 297. formation of, 3. hardness of, 29-30. heat resistivity of, 32. in electrical insulation, 23-34. in Hindu chemistry, 96. - in different countries, 135. - in war, 107, 114–115.

^{*} Mica Directory and Who's Who in Mica by R. R. Chowdhury, Post Box No. 11437, Calcutta (under preparation).

Mica merchants, 103. – mining of, 58. – paper, 250–251. - percussion and pressure figures of, 17. ---- pleochroism in 29. properties of, 281. prospecting of, 42. - splitting (see splittings). machine, 226. - synthetic, 275. - tape, 252 - tubing, 253-254. types of, 142. Micalite, 258. Micarta, 273. Microcline, 14, 46, 181. Microfarads, 285. Micron, 276. Middle average, 212. Middlemen, 307. Mining, 54, 65, 73, 77, 170. ————— centres, 117–118, 122–123. - equipment, 159. - modern, 59. - reason, 156. - rent and royalty, 121. - rules, 57 Mineral stains, 192. Mine-run mica, 83, 85-86. Monghyr, 118. Morning Star mine, 149. Motor, 277. Moulding micanite (insulation), 246, 262, 296. Mozambique, 172. Munition, 115. Muscovite mica. 10, 18, 21, 45, 135, 137, 149, 185, 202, ———— mica plate, 262. ———— sources of, 2, 137, 185. Muscovitisation, 5. Muscovy glass, 17. Mycalex, 273-274. Mysore, 132. N Namaqualand, 172. Nandgaon State, 129. Narukot, 133. Natal, 169. Nellore, 101, 122. Neon light (signs), 258, 284. Newfoundland, 162. New Hampshire, 149, 152. New Jersey, 152. New Mexico, 152.

н, м

New South Wales, 177. New York, 152. Nilgiris, 124. North Carolina, 150. North Hill mine, 159. Northern Australia, 175. Northern Rhodesia, 171. Norway, 183. Nyasaland Protectorate, 172. O Occurrence of mica, 96-189.

Occurrence of mica, 96-189. - mode of, 7. - of mica in Afghanistan, 139. Argentina, 162. Austria, 183. Bolivia, 16 Brazil, 163. 161. Burma, 133. Camerons, 171. Canada, 153. Cape Colony, 169. Ceylon, 137. Chile, 162. China, 138. Chosen, 135. Cochin China, 139. Costa Rica, 162. Czechoslovakia, 184. England, 183. - Ethiopia (Abyssinia), 172, German East Africa (Tanganyi-ka), 173. Germany, 183. Guatemala, 161 India, 96. Japan, 136. Kenya Colony, 171. Madagascar, 164. Mexico, 162. Mozambique, 172. Namaqualand, 172. — Natal, 169. — New South Wales, 177. - Newfoundland, 162. New Zealand, 177. - Norway, 183. Nyasaland Protectorate, 172, --- Peru, 161. Portugal, 183. 22

Occurrence of mica in Queensland, 176.
Rhodesia, 169.
171.
Rumania, 183.
——————————————————————————————————————
——————————————————————————————————————
Union, 166.
South West
Africa, 171.
1//.
Sweden, 183.
Switzerland, 188.
Tanganyika, 173.
Tasmania, 177.
——————————————————————————————————————
Transvaal, 167.
United States,
139.
Oil engine, 34.
Oliphants river mica field, 157.
Open-cut (or open quarry), 60-61,
66, 156.
Optic axial angle, 25.
Orthoclase, 14, 46.
Output sales, 305.
Overhead expenses, 103.

P

Packing, 264, 303. Paint industry, 236. Palamau, 119. Pale green mica, 203. Pallermo mine, 150. Pallimitta mine, 123. Panpacked splittings, 221. Parafin as insulator, 35. Paragonite mica, 188. Pascoe, Sir Edwin, 316. Patented roofing, 235. Patiala, 130. Payment (terms of), 303. Pearson mine, 150. Peerless mine, 153. Pegmatite, 3, 6, 12, 43, 78. Percolators, 208. Percussion figure, 16–17. Pertinex, 34, 272. Peru, 101. Petering out, 45. Phlogopite mica, 15, 19, 23, 65, 135, 187. Peru, 161. Phosphate, 153-154. Physical properties of mica, 16, 21–23. Piedmont mica belt, 150. Pike Lake mine, 160,

Pioneers, 120, 126. Pitchblende, 272. Plastic specialities, 236. Pleochroism in mica, 29. Pockety deposit, 8. Porphyry, 4. Portugal, 183. Portuguese East Africa (Mozambique), 172. Potash mica (see muscovite). Powder loose splittings (see dust loose). Powell mine, 150. Power drill, 68. ----- factor in electric insulation, 37, 281. Pressure figure, 16–17. - test, 263. Price of mica, 305, 329-332. Production of mica, 303, 329-332. Production of mica, 42. statistics, 106, 108, 110, 144, 237, App. VII.. Property of mica, 22-23. Prospecting, 42, 47. Punch, 214. Pyrite, 15. Pyroxene, 1, 19.

Q

Quality of mica, 120, 125, 138, 159. Quartz, 1, 44-45. Queensland, 176.

R

Radio, 257. . 1 ----- transmitter, 290. Rajputana, 127. Ray mine, 141, 154. Reclamation of mica, 70-71, 94-95. Recovery of mica, 75, 230-231. Rectangles, 214. Red spotted black-stained mica, 204. - mica, 204. Reference, 300. Refractive index, 22–25. Rent (and Royalty), 121, 125, 318. Research Corporation, 275. Reserve forest, 49, 95. Resources of mica, 283, 308. Retrospect, 314. Rewa State, 130. Rhodesia, 169. Ring condenser insulation, 290. Rock formation, 5. — mine, 151. Rocks, different types of, 1. Roofing components, 235. Rope paper and mica, 251.

Index

Ropeways, 70. Rosscie mine, 165. Rossie mine, 165. Rotary trimmer, 199. Rough mica, 75-77, 81, 89, 79, 157, 208. Royalty (see rent). Rubber trade, 236. Rubidium, 184. Ruby mica (see muscovite mica). Ruggles mine, 149-150. Ruled mica, 191. Rumania, 183. Run-of-mine mica, 167. Russambo field, 169. Russia, 179, 311. Rutile, 269, 275.

S

Sachenga mine, 171. S. D. B. mica, 76, 193–195, 200. Sahana, Rajkrishna, 122. Sailor's hat, 165. Samarskite, 272. Sambalpur, 119. Sankara mine, 80, 123. Santal Parganas, 119. Saphi mica field, 118. Scrap mica, 143, 309. Secondary mica, 3. Second-class mine, 53-54. Segment, 208. Selected-to-cut mica, 213. Sericite, 3, 268. Serpentine, 19, 269. Shaft house, 129, 159. Shaft working, 141, 156. Shahapura State, 129. Shallow forking, 50. Shallow torang, 198. Shear trimming, 198. Sheet mica, 2, 6, 101, 143, 208, 284-86, 309, 311. consumption of, 311. Shipment block, 199. Siberia, 179. Sickle cobbing, 196. - dressing, 208. advantages of, 195. Sikkim-Tibet, 128. Sillimanite, 4. Silver amber, 206. Silver speckled white, 203. Silverleaf mine, 161. Singbhum, 119. Sirohi, 130. Sizes of mica, comparative, 215. Slightly stained mica, 204. Socialism, 57.

Soft white mica, 203, 206. Somaliland, 171. Sorting of mica, 202. South African Union, 166, 171. - Carolina, 151. Dakota, 153. Southern Rhodesia, 169. Soviet Russia, 177. Sparking plug insulation, 293. Specific gravity, 23-24. Specifications, 39, 256. - of ground mica, 267. - of "N-E-M-A", 327. - of micanite, 259. - of splittings, 264, 327. Splittings, 309. _____ block, 199. bookform, 221. Canadian, 220, 226. dust loose, 224. Indian ruby, 220. loose packed, 223. - Madagascar, 165, 206, 227. - panpacked, 221. - square packed, 222. - U. S. A., 225. Spodumene, 5, 19. Spotted green, 203. — mica, 163 202, Stained mica, 202. Standardisation, 103-104, 314-318. Star mine, 150. Statistics, 106–108. Stealite, 269. Steam pipe insulation, 33. Stoness mine, 160. Stoping, 62, 149, 158. Stove mica, 208, 257. Substitute of mica, 34, 272. Supervision in mica, 92. Sweden, 183. Switzerland, 188. Synthetic mica, 275.

Т

Taggart mine, 160. Talc, 269. Tallabodu mine, 123. Tanganyika territory, 173. Tangle sheet or tangle foot, 191. Tantalite, 44, 272. Tariff on mica, 246, 256, 325. Tasmania, 177. Technique of mica marketing, 300. Terms of business, 303. Testing of mica, 37, 256. Texas, 153. Thermal resistance, 22–23, 32.

Handbook of Mica

Thikadars, 48. Thin split mica, 199. Third-class mine, 53. Thumb-trimmed mica, 195-196. Tibet, 139. Toasters, 208. Tonk, 130. Topaz, 18. Tourmaline, 12-13, 44, 174, 271. Traction, power for, 71. Transformer; 40. Transvaal, 167. Travancore, 126. Trenching, 43, 52. Triphylite, 184. Triplite, 272. Tunnels, 43. Turbonite, 272. Turpentine, 35.

U

Udaipur State, 131, 204. Uncut condenser mica, 213. Underground mining, 64. Union mica, 150. Union of South Africa, 166. United States, 139, 310, 313. Uparchala, 48, 100, 102. ———— mining, 48–49. Uranium ochre, 272. Use of mica, 208, 276, 281, 295, 316.

V

Valencia mine, 150. Vanadium mica, 20. Vein deposit, 7, 64. Vermiculite, 16, 136, 269. Virginia, 153. Vizagapatam, 124. Voltmeter, 41. Volume resistivity, 280. Vulcanite beston, 35.

W

Wall paper trade, 235. Wallingford mine, 153. 159. Walnut Knob mine, 156. Warehouse and wharfingers, 302. Warehouse charges, 322-323. Wastage, 74, 82-92. Wedge mica, 15, 191. Weights, currencies and measures, 324. Western Australia, 25, 175. Wet grinding process, 233. Wheat mine, 150. White Star mine, 153. Winning of mica, 66. Wireless, 34. ______ outfits, 257.

х

Xenotime, 272.

Y

Yenadis of Madras, 59.

Z

Zamindary land, 49, 100, 126. Zigzag cutting, 191. Zinnwaldite mica, 18, 188, 137.

INDIA MICA, VOL. I

By Ramani Ranjan Chowdhury, Mica Specialist.

Price Rs. 5 or 7s. 6d. net, postage extra.

Opinions, Far and Wide.

L. G. Banker, Esqr., SCHENECTADY, N. Y. (Late General Purchasing Agent, GENERAL ELECTRIC COMPANY, SCHENECTADY, N. Y.), writes :--

> "Your book covers the mica industry quite fully from its origin and composition to the procedure of mining and preparing it for use by the various classes of consumers. The different operations are described quite accurately and it is one of the very few and the most complete HANDBOOK on Mica so far published.

> "It is a creditable production for, in addition to the historical and scientific matters, there are clear instructions as to processing and the various grades and qualities with which the market is served. The book ought to be helpful in giving interest and information to the Indian producers and to the consumers of the world."

J. Fuller Brown, Esqr., of the Asheville Mica Co., U. S. A., writes :---

"It has been a pleasure reading your First Volume of India Mica and you are to be commended on this work. In reading over the references listed in the back of your book, the writer feels that you have already brought together such informations as to preclude our contributing anything more of a constructive nature. I will look forward with much pleasure to receiving a copy of the Second Volume, for which we have already placed an order."

William Naumberg, Jr., Esqr., of William Brand & Co., N. Y., writes :---

"I appreciate the book and it is to my mind a very welcome contribution to a subject about which little has been written. It shows the result of much painstaking study and efforts in its compilation."

H. V. Wilczek, Esqr., of Boston, U. S. A., writes :--

"The book itself is wonderfully concepted and splendidly executed, surely the very finest thing I have ever seen in connection with the material in question. It should be a great help to many engaged in that business. In spite of accumulating quite some library on the subject of Mica, I do not know of any single book that could favourably compare with the fruit of your ardent labour and deliberation. In regard to your book itself, there is no doubt in my mind that it will be and should be acted upon as a standard for all interested in mica, be on your side or anywhere in the world, where mica is being found and traded."

Dr. Hepner of Messrs. Jaroslaw's Erste Glimmerwarenfabrik in Berlin writes :--

"Your book is very interesting even for persons who have been such a long time in the mica business like myself and who has learned from your book several things and which I did not know, although I am now since 27 years in this trade." John R. Rettig, Esqr., Sweden, writes :--

"I am glad I ordered this book for, as a fact, I consider it the best source on this topic I ever had in my mind. The contents are remarkably comprehensive for a little book of 103 pages with Appendix; it is as clear as crystal and everything speaks of a reliable authority. I am sure it will cause great success in quarters interested in this article. Please let me have the Second Volume referred to."

Dr. Alfredo Landsberg of Milano, Italy, writes (30-10-33) :--

"I have now pleasure in informing you that your publication has very much satisfied me and that I consider it without exaggeration, as the best publication actually existing in this line. Your book contains valuable informations also for those since long in our trade and I have to admit that I found in your book certain facts I ignored so far.

"I am now awaiting the publication of the Second Volume but I doubt the thoroughness and completeness of the first one can be surpassed."

N. J. Greene, Esqr., of the National Electric Coil Co., of U. S. A. (30-4-36), writes :--

"We found your book of unusual interest because it is written from the view-point of one living in India, making it most valuable for a user of mica splittings, far removed from the source of supply. While we have quite a collection of data on mica as related to its properties and micanite manufacturing processes, we have very little data on various handlings prior to export. Kindly book us for one copy of "Vol. II" dealing with Mica in other countries."

E. Watson, Esqr., of WATSON BROTHERS of New York and now General Manager of Messrs. F. F. Chrestien & Co., Ltd. (24-12-35), writes :--

"I hasten to thank you for the copy of your India Mica which I shall read with great interest and treasure with much appreciation. You are to be congratulated on your industrious efforts to get together the materials for your book and to present them so graphically. Your own book must have done much to educate the consumers of mica."

Mr. Gavin Lawson, London, writes :---

"I duly received the copy of *India Mica*, Vol. I, by Dr. R. R. Chowdhury, for which I thank you. I have not yet had an opportunity to read the work carefully but I have consulted it already on several points which have arisen and found the information for which I sought. I have no doubt that it will prove useful when information on the less common details is also needed."

Indian Opinions.

"This handy volume (India Mica, Vol. I) on mica supplies a real want. * * * Mr. Chowdhury's treatise gives particulars about the different sources of mica in the country and deals with the preparation of the stuff for the market, its uses and properties. There is a good amount of information packed in the hundred and odd pages of the book, besides twelve appendices, which are themselves greatly informative. "We commend this book to the public as a substantial contribution in a field not frequently traversed by writers."—The Hindustan Times, Delhi, 12-6-1932.

"There are many in this country who might have heard the name of mica, but have never seen it. There are again many who have seen it but are unaware of its manifold uses. * * It is to be regretted that we had so long practically no informative book, except scrappy bulletins issued from time to time by the Mining, Geological and other Departments on the Mica Industry, which shows signs of rapid increase. We are glad that this long-felt want has been removed by Sj. Ramani Ranjan Chowdhury, whose book "India Mica" will be considered really useful to those who are in the trade as well as to those who are interested in the future of this useful mineral. The writer has made a special study of the subject and his articles in the Amrita Bazar Patrika some years ago evoked interest from many quarters. Sj. Chowdhury's book is worthy of consideration, for the mica industry has great possibilities before it."—The Amrita Bazar Patrika, 19-4-1932.

"The author of *India Mica*, Mr. R. R. Chowdhury, is not an amateur in this subject. He is already well known to the readers of Calcutta newspapers from the series of articles on Mica which he has been contributing to the press from time to time and now he presents to the public of our country for the first time, a connected account of what this important mineral is and what it might be for India. * * Our purpose is to endorse the view of Mr. Chowdhury that the Mica Industry promises a great future for India."—*The Advance*, Calcutta, 19-4-1932.

"The book (India Mica, Vol. I) is full of noteworthy factors which have been treated with adequate details and there are important discussions on valuable commercial and industrial practices which demand proper attention of the people concerned. The statistical figures are recorded up to 1931 for India and to 1928 for other countries. There are seven chapters besides the introductory chapter and the appendices. * * * Both Dr. Coggin Brown and Mr. Hobson condemned the bad trade practices of some of the Indian firms and the latter in addition mentioned that a feeling of doubt as to the security of Indian supplies was spreading amongst consumers and he solicited immediate intervention of proper authority. Mr. Chowdhury in his book sounds the signal of danger. He has given his experience in India of the prevalent malpractices and has pointed out the loopholes and latitudes in the present system of grading according to size and quality, which the unscrupulous dealers utilise to their advantage. * * These malpractices can be checked most effectively by legislation and controlling boards like marketing boards.

"Mr. Chowdhury deserves thanks of all conscientious mica merchants for suggesting practical methods to uplift the mica trade of India and to regain mutual confidence. The volume is sure to attract attention of the public as it places before them the technique and prospects of the Indian Mica Industry."-Modern Review, July, 1932, by Prof. S. L. BISWAS, M.Sc., Head of the Department of Geology, University of Calcutta. "I have been reading with interest your monograph on India Mica, Vol. I. I am glad to find that you have collected within its narrow compass valuable informations and data on this important mineral. I hope in these hard days of unemployment, many of the educated and enterprising young men may find useful hints and lines of occupation by going through your book.

"You have done a patriotic service by writing this book and I trust your efforts will bear fruit. I look forward to the proposed Vol. II."—SIR P. C. Roy, KT., D.Sc., F.C.S., 29-6-1932.

"I have read with great pleasure the book India Mica, Vol. I. Being connected with the commercial side of the industry for a long period, the author has collected a mass of invaluable informations regarding it. His informations are thoroughly reliable and accurate. * * * In writing this book, the author has done really a service to our land in bringing before our countrymen the enormous possibilities of this important economic mineral."—Prof. P. N. GHOSH, M.A., Ph.D, Sc.D., Head of the Department of Applied Physics, University College of Science, Calcutta.

Prospects of the Cane Sugar Industry in Bengal by the same author*

Price Rs. 2 net.

"Mr. Chowdhury puts in a passionate and at the same time able plea for the development of the Sugar Industry in Bengal. He draws pointed attention to some of the fallacies and inaccurate bases of information underlying the Tariff Board's Report and not only criticises the Bengal Government's lack of enthusiasm but puts forward definite suggestions for the cultivation of sugar cane and the organisation and development of the Sugar Industry in the province."—*The New Review*, 1938.

"Mr. Chowdhury in this brochure, illustrates by facts and figures the great possibilities of the industry in this province and in doing this the author took great pains in studying the subject in all its aspects from the field to the factory and from factory to the consuming market. The author points out in no unmistakable terms the defects in the Protection Act and the recommendations of the Tariff Board and the Imperial Council of Agricultural Research in respect of Bengal. The present book is full of instructive and informative details which demand its wide publicity to all those interested in the conomic progress of Bengal."—The Financial Times, February 1939.

*To be had of R. R. Chowdhury & Co., Post Box 11437, Calcutta, India.

INTERNATIONAL COMBUSTION

MICA MINING GRINDING and BOILER EQUIPMENT Water Tube Boilers Mechanical Stokers Coal, Ash and Material Handling Plant Grinding Plant Grinding Plant : : Air Separating Plant Wet Grinding and Classifying Plant : : Electrical and Mechanical Screens Grit Pumps, etc., etc.



7, CHURCH LANE, CALCUTTA

Mica and India Minerals

We are suppliers of

"R. R. C." Marks, which are well known in international trade. Materials ordered with us are packed under the guidance and supervision of Mr. R. R. Chowdhury, the worldrenowned Mica Specialist. We supply goods to selected clients, who care more for fair dealings and standardised merchandise, rather than running after cheap trash with endless bargaining.

Terms: Letters of credit, quotation and samples on request.

R. R. CHOWDHURY & CO.

Post Box No. 11437, Calcutta, India.